

TECHNICAL DATASHEET COATING MASS BMA

Product description

Dosteba Coating mass BMA, coating adhesive for polystyrene profiles

Scope of application

Coating mass for facade profile Do-Pro especially for closing butt joints and mitre joints.

Characteristics

- shockproof (not impact-resistant)
- paintable
- high levels of strength
- permanently elastic
- UV-stable

Technical data

Consistency:	pasty, firm
Colour:	beige
Density:	approx. 1,6 – 1,8 g/ml
Open time:	approx. 30 minutes (23 °C / 55 % RH)
Curing:	up to max. 3 mm layer / 24 h (23 °C / 55 % RH)
Application temperature:	min. > 5 °C max. 30 °C >= 12 °C
Temperature resistance:	-20 °C to +90 °C
Tensile strength:	> 0,1 N/mm ²
Shock resistance:	5 kJ
Shock resistance and ultimate tensile strength:	Stronger mechanical impacts and strong bending stresses result in deformation and breakage and should therefore be avoided.
Shelf life:	12 months / min. +5 °C
Container:	Bucket
Content:	1kg or 5 kg

Processing instructions

The substrates to be bonded must be free of dust, grease and oil and must also be solid and capable of bearing the load.

Special instructions

The labelling of the product in accordance with Regulation (EC) No. 1272/2008 (CLP) can be found in the safety data sheet.

Further instructions are available on the latest safety data sheet.

The information on our technical data sheets is based on our experience and current state of knowledge. It is your responsibility to test the suitability of our products for your intended use. Dosteba AG and Dosteba GmbH disclaims all liability for consequential damages.